


DATASHEET

Breakout I-V(ZN) HH OM2 50/125µm ST/SC 2G 1,0m



General data

Characteristics and advantages of Trunk cables:

- 2 up to 48 fibers per cable (other Trunks available on request)
- Pre-assembled, polished and factory-tested
- Both-sided assembled with stepped plug whips
- Ready to use, no need for expensive splice- and measuring equipment
- With Premium or Standard cable divider at customers choice
- Attenuation protocol for each assembled connector included in delivery
- All possible combinations of connectors like LC, E2000®, SC and ST available
- Identification with cable markers
- Delivery depending on length and type: one way drum or cable ring

Technical properties

Category	OM2
Coding	1:1
Colour outer sheath	orange
Connector connection 1	ST
Connector connection 2	SC
Crossed	No
Fibre type	OM2 50/125
Flame retardant	nach EN 50266-2-4
Halogen free (according to EN 50267-2-3)	True
Material outer sheath	LSZH
Operating temperature	-20 - 60 °C
Storage Temperature	-25 - 70 °C
With rodent protection	False

Available variants

ArtNr.	Bezeichnung	Length	Number of connectors connection 1	Number of connectors connection 2	Number of fibres
--------	-------------	--------	---	---	---------------------

This datasheet was created automatically on 25-09-2026 . Technical changes reserved.



DATASHEET

Breakout I-V(ZN) HH OM2 50/125µm ST/SC 2G 1,0m

O9811.1	Breakout I-V(ZN) HH OM2 50/125µm ST/SC 2G 1,0m	1.0 m	2	2	2
O9831.1	Breakout I-V(ZN) HH OM2 50/125µm ST/SC 4G 1,0m	1.0 m	4	4	4
O9851.1	Breakout I-V(ZN) HH OM2 50/125µm ST/SC 8G 1,0m	1.0 m	8	8	8
O9871.1	Breakout I-V(ZN) HH OM2 50/125µm ST/SC 12G 1,0m	1.0 m	12	12	12

Note on Intended Use

This data sheet is intended solely to describe the technical characteristics of the product. It does not replace an assessment of the product's suitability for a specific application. The user is responsible for ensuring that the product is used in accordance with its technical specifications and applicable legal and regulatory requirements.

This datasheet was created automatically on 25-09-2026 . Technical changes reserved.

